



Hoja Datos Producto

Colorante DuPont™ Artistri™ - Propiedades Usuario Final

Tipo Colorante: **Ácido DuPont™ Artistri™ Serie 700**

Tipo tejido: **Nylon/Lycra®**

Resultados Individuales Colorantes														
Nombre Prueba	Nº ID Prueba	C A774	M A715	Y A746	K A795	N A768	FIY A755	FIR A745	Ltk A793	B A776	O A737	sC A773	Ltm A714	LtsC A772
Solidez al lavado (50C)	AATCC 61 (ISO105-C06)													
	cambio de tono	4-5	5	5	4-5	4-5	4-5	4-5	5	4	4-5	4-5	5	4-5
	transferencia color													
	seda	5	4-5	5	4	4	4	4-5	5	3	5	5	5	5
	lana	5	5	5	4-5	5	3-4	4-5	5	4-5	5	5	5	5
algodón		5	5	5	4-5	3-4	2	5	5	4-5	5	4-5	5	5
	nylon	5	5	5	4-5	3	4-5	5	5	3-4	5	5	5	5
Transpiración ácido	AATCC 15 (ISO105-E04)													
	cambio tono	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	5	5
	Transferencia color													
	seda	5	5	5	5	5	5	4	5	5	5	5	5	5
	lana	5	5	5	5	5	5	4	5	5	5	5	5	5
algodón		5	5	5	5	5	4-5	4-5	5	5	5	5	5	5
	nylon	5	5	5	5	5	4-5	4-5	5	5	4-5	5	5	5
Agua de mar	AATCC 106 (ISO 105-E02)													
	cambio de tono	4-5	5	5	4-5	4-5	4	4-5	4-5	4	4	4-5	4-5	3-4
	transferencia color													
	seda	5	5	5	4-5	5	1	2	5	4	5	5	5	4-5
	lana	5	5	5	4-5	5	2	2-3	5	3-4	5	5	5	4-5
algodón		5	5	5	4-5	5	1	2-3	5	3-4	5	5	5	4-5
	nylon	5	5	5	4-5	5	1	1-2	5	3	5	5	5	4-5
Solidez color al agua	AATCC 107 (ISO105-E01)													
	cambio tono	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	5	5	4-5
	transferencia color													
	seda	5	5	5	5	5	3	3	5	5	5	5	5	5
	lana	5	5	5	4-5	5	3-4	4-5	5	5	5	5	5	5
algodón		5	5	5	5	5	2-3	4	5	5	5	5	5	5
	nylon	5	5	5	5	5	3	3-4	5	5	4-5	5	5	5
Agua clorada	AATCC162 (ISO105-E03)													
	cambio tono	5	5	4-5	4-5	4-5	3-4	3	5	4-5	4-5	3-4	5	2-3

Resultados Individuales Tintas

Nombre Prueba	N° ID Prueba	C A774	M A715	Y A746	K A795	N A768	FIY A755	FIR A745	Ltk A793	B A776	O A737	sC A773	Ltm A714	LtsC A772
Solidez a la luz (lámpara Xenon 20 h.)	AATCC 16 (ISO 105-B02)	2	4-5	5	5	5	2-3	2-3	4-5	4	4	2	2-3	2
Solidez a la fricción mojado y seco	AATCC 8 (ISO 105-X12)	4/5	4.5/5	5/5	4.5/5	5/5	4.5/5	4.5/5	4.5/5	5/5	5/5	5/5	5/5	5/5
Transpiración álcali	ISO 105-E05													
	cambio tono	5	4-5	4-5	4-5	5	4-5	4-5	5	5	4-5	5	5	4-5
	transferencia color													
	seda	5	5	5	5	5	2-3	3	5	5	5	5	5	5
	lana	5	5	5	5	5	2	4-5	5	5	4-5	5	5	5
	algodón	5	5	5	5	5	1-2	4-5	4-5	5	5	5	5	5
	nylon	5	5	5	5	5	2	4-5	5	5	4-5	5	5	5

The information has been carefully compiled from experience gained in the laboratory and under commercial conditions. However, the product's performance and its suitability for the customer's purpose depend on the particular conditions of use. We recommend that customers satisfy themselves that each product meets their requirements in all respects. This information is being provided by DuPont free of charge as a courtesy to DuPont's customers, and DuPont HEREBY DISCLAIMS ALL REPRESENTATIONS, WARRANTIES AND LIABILITIES WITH RESPECT TO THE INFORMATION AND USE THEREOF. Subject to change without notice. All sales are subject to our standard terms and conditions of sale.

DuPont Ink Jet · Barley Mill Plaza · PO Box 80030 · Wilmington, DE 19880-0030

Artistri.DuPont.com | US 1.877.234.1794 or 1.302.992.4264 | Asia 65.6586.3699 | Europe 39.02.2530.2657

© Copyright 2003, Rev. 2004. E.I. du Pont de Nemours and Company. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™ and Artistri™ are registered trademarks or trademarks of DuPont or its affiliates. Lycra® is a registered trademark of INVISTA.

K-04380-4 10/04



The miracles of science™